M Plus J627

Carbon 01

Specifications

Contents
100% polyester

Weight
18.7 ± 1.5 oz./sq. yd.

Width
sold in specific dimensions

Repeat
none

Treatment
none

Backing
none

Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May be cleaned with a 10% solution of concentrated household bleach. Rinse thoroughly with clean water after each application. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners. Read the Cleaning & Disinfection Handbook.

Performance

Breaking Strength (ASTM D5034)
175 lbf min. warp and fill

Tear (ASTM D2261)
30 lbf min. warp and 35 lbf min. fill

Pilling resistance (ASTM D3511)
Class 4 min.

Colorfastness to light (AATCC 16.3 Option 3)
Grade 4 min. at 40 hours

Colorfastness to crocking (AATCC 8)
Grade 4 min. dry & Grade 3 min. wet

Wyzenbeek Abrasion resistance (ASTM D4157)
200,000 double rubs min. cotton duck

Flammability
CA Technical Bulletin 117-2013 Section 1

Miscellaneous

Every effort has been made to ensure color accuracy of the digital images, however, please order a sample before specification. Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric. 10 year performance warranty.

Proudly knit in North America supporting our local communities.

Teknit is our unique knitting process that produces dimensional form fitting fabric covers and suspension parts that improve the ergonomics, comfort and design of a chair.

Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.



Guilford of Maine